

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L1	12	"1029901"	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 09:46
L2	20	"0270472"	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 09:46
L3	9	"270472"	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 09:47
L4	0	"061223"	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 09:47
L5	40	"0061223"	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 09:47
L6	10	"61223"	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 10:56
L7	2	"16243"	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 09:48
L8	3	(Haines.in. or (Textured near2 Coatings).as.) and ((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer or pigment or oxide or TiO2 or "TiO.sub.2"))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:43
L9	2	(Haines.in. or (Textured near2 Coatings).as.) and ((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (building or house or architect\$9 or wall))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:01
L10	2	(Haines.in. or (Textured near2 Coatings).as.) and (((external or vertical or outside or exposed) near2 wall) with (paint\$5 or coat\$5 or deposit\$5 or film or layer or pigment or oxide or TiO2 or "TiO.sub.2"))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:06
L11	1	(Haines.in. or (Textured near2 Coatings).as.) and ((tex adj cote\$5) or (super adj cote\$5) or (trim adj cote\$5))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:04

L12	1	(Haines.in. or (Textured near2 Coatings).as.) and ((tex near2 cote\$5) or (super near2 cote\$5) or (trim near2 cote\$5))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:05
L13	2	(Haines.in. or (Textured near2 Coatings).as.) and ((tex near2 cote\$5) or (super near2 cote\$5) or (trim near2 cote\$5) or "tex.cndot.cote" or "super.cndot.cote" or "trim.cndot.cote")	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:06
L14	47	(Haines.in. or (Textured near2 Coatings).as.) and ((energy or cool\$4) with (paint\$5 or coat\$5 or deposit\$5 or film or layer or pigment or oxide or TiO2 or "TiO.sub.2"))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:07
L15	678	(427/160).CCLS.	US-PGPUB; USPAT	OR	OFF	2006/02/01 11:42
L16	1639	(427/180,205).CCLS.	US-PGPUB; USPAT	OR	OFF	2006/02/01 11:42
L17	899	(427/419.2).CCLS.	US-PGPUB; USPAT	OR	OFF	2006/02/01 11:43
L18	206	(106/712).CCLS.	US-PGPUB; USPAT	OR	OFF	2006/02/01 11:43
L19	452	(106/287.19).CCLS.	US-PGPUB; USPAT	OR	OFF	2006/02/01 11:43
L20	516	(106/400,401).CCLS.	US-PGPUB; USPAT	OR	OFF	2006/02/01 11:43
L21	4325	15 16 17 18 19 20	US-PGPUB; USPAT	OR	ON	2006/02/01 11:43
L22	1	21 and ((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer or pigment or oxide or TiO2 or "TiO.sub.2")) and ((external or outer or outside or exposed) with vertical with wall with (building or architectur\$9 or house))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:45
L23	24	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer or pigment or oxide or TiO2 or "TiO.sub.2")) and ((external or outer or outside or exposed) with vertical with wall with (building or architectur\$9 or house))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 11:50

L24	377	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer or pigment or oxide or TiO2 or "TiO.sub.2")) same ((external or outer or outside or exposed or vertical) near5 wall)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:44
L25	18	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer) same ((oxide or inorganic or TiO2 or "TiO.sub.2") with (pigment or \$7particle or \$7powder or color\$5))) and ((coat\$5 or deposit\$5 or paint\$5 or apply\$5 or application) with (wall) with (outer or exposed or vertical or outside or exterior))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 12:18
L26	145	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer) same ((oxide or inorganic or TiO2 or "TiO.sub.2") with (pigment or \$7particle or \$7powder or color\$5))) and ((coat\$5 or deposit\$5 or paint\$5 or apply\$5 or application) with (wall or architectur\$9 or building or facade))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:45
L27	127	26 not 25	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 12:18
L28	0	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer) same ((oxide or inorganic or TiO2 or "TiO.sub.2") with (pigment or \$7particle or \$7powder or color\$5))) and (paint with (solids) with weight with volume with (optim\$9 or determin\$9 or depend\$8 or prefer\$8 or best))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:26

L29	1	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer) same ((oxide or inorganic or TiO2 or "TiO.sub.2") with (pigment or \$7particle or \$7powder or color\$5))) and (paint with (solids) with weight with volume)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:21
L30	0	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer) same ((oxide or inorganic or TiO2 or "TiO.sub.2") with (pigment or \$7particle or \$7powder or color\$5))) and (paint with (solids) with (weight or volume or percent or "%") with (optim\$9 or determin\$9 or depend\$8 or prefer\$8 or best))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:22
L31	7	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer) same ((oxide or inorganic or TiO2 or "TiO.sub.2") with (pigment or \$7particle or \$7powder or color\$5))) and ((solids) with (weight or volume or percent or "%") with (optim\$9 or determin\$9 or depend\$8 or prefer\$8 or best))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:23
L32	92	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer)) and ((solids) with (weight or volume or percent or "%") with (optim\$9 or determin\$9 or depend\$8 or prefer\$8 or best))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:24
L33	2	(paint with (solids) with weight with volume with (optim\$9 or determin\$9 or depend\$8 or prefer\$8 or best))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:27
L34	9	(paint with (solids) with weight with volume same (optim\$9 or determin\$9 or depend\$8 or prefer\$8 or best))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:29

L35	96	(paint with (solids) with (weight or volume) with (optim\$9 or determin\$9 or depend\$8 or prefer\$8 or best))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:33
L36	20	(25 or 26) and primer	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:42
L37	4	24 and primer	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:44
L38	22	((IR or infrared or heat or sun or sunlight or radiation or solar) near2 reflect\$5 with (paint\$5 or coat\$5 or deposit\$5 or film or layer) same (wall or facade or building or architect\$9)) and (primer with (prefer\$9 or desir\$8 or benef\$8 or advantag\$8))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:47
L39	0	paint\$5 same (primer with (prefer\$9 or desir\$8 or benef\$8 or advantag\$8)) same (primer with (white)) same (primer with (textured))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:48
L40	0	paint\$5 same (primer with (prefer\$9 or desir\$8 or benef\$8 or advantag\$8)) and (primer with (white)) and (primer with (textured))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:48
L41	769	paint\$5 same (primer with (prefer\$9 or desir\$8 or benef\$8 or advantag\$8))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:48
L42	17	paint\$5 same (primer with (prefer\$9 or desir\$8 or benef\$8 or advantag\$8)) same (primer with white)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:50
L43	30	paint\$5 same (primer with (prefer\$9 or desir\$8 or benef\$8 or advantag\$8)) and (primer with white)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:54

L44	36	paint\$5 same (wall or building or architec\$8 or facade) same (primer with (prefer\$9 or desir\$8 or benef\$8 or advantag\$8))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 13:57
L45	243	paint\$5 same (primer near3 (prefer\$9 or desir\$8 or benef\$8 or advantag\$8))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:00
L46	13	paint\$5 same (primer with (prefer\$9 or desir\$8 or benef\$8 or advantag\$8 or depend\$8 or optimiz\$8 or optim\$9) with white)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:02
L47	272	paint\$5 same (primer with white)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:16
L48	9	paint\$5 same (primer with white) same (wall or building or architec\$8 or facade)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:05
L49	36	(paint\$5 same (primer with white)) and (paint\$4 with (wall or building or architec\$8 or facade))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:05
L50	1	("4546007").PN.	US-PGPUB; USPAT	OR	OFF	2006/02/01 14:14
L51	2	paint\$5 same (primer with (wet near2 thickness) with mil)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:17
L52	21	(primer with (wet near2 thickness) with mil)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:21
L53	4	(primer with (wet near2 thickness) near4 (prefer\$8 or depend\$8 or determin\$8 or advantag\$8 or optim\$9 or benef\$8))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:22

L54	12	(primer with (wet near2 thickness) with (prefer\$8 or depend\$8 or determin\$8 or advantag\$8 or optim\$9 or benefi\$8))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:26
L55	83	(primer with (wet near2 thickness))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:23
L56	415	(primer with (thickness) with (prefer\$8 or depend\$8 or determin\$8 or advantag\$8 or optim\$9 or benefi\$8))	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:27
L57	35	56 and (wet near2 thickness)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:30
L58	2	(textured near2 primer) with (benefi\$9 or advantag\$8 or prefer\$8 or desir\$8 or optim\$9)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:32
L59	55	(textured near2 primer)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:39
L60	14	(primer) with (square near2 feet) near3 gallon	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:41
L61	9	(primer or paint\$5) with ((square near2 feet) near3 gallon) with (determin\$9 or depend\$8 or based or choose or chosen or choos\$5)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:45
L62	29	(primer or paint\$5) with ((square near2 feet) near3 gallon)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:43
L63	76	((square near2 feet) near3 gallon) with (determin\$9 or depend\$8 or based or choose or chosen or choos\$5)	US-PGPUB; USPAT; EPO; JPO; DERWENT; IBM_TDB	OR	ON	2006/02/01 14:45